

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
6 October 2005 (06.10.2005)

PCT

(10) International Publication Number
WO 2005/093126 A1

(51) International Patent Classification⁷: C23C 16/40,
16/34, 16/30, 16/448

(21) International Application Number:
PCT/IB2005/000522

(22) International Filing Date: 24 February 2005 (24.02.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/550,908 5 March 2004 (05.03.2004) US
2004-193710 30 June 2004 (30.06.2004) JP
10/939,269 10 September 2004 (10.09.2004) US

(72) Inventors; and

(75) Inventors/Applicants (for US only): MISRA, Ashutosh [IN/US]; 2425 Hunters Run Drive, Plano, TX 75025 (US). FISHER, Matthew [US/US]; 417 St. Andrews Drive, Allen, TX 75002 (US). JURCIK, Benjamin [US/US]; 2415 Canyon Creek Drive, Richardson, TX 75080 (US). DUSSARRAT, Christian [FR/JP]; Tsukuba-Matsushiro 4-2-1 #204, 4-15-2, Matsushiro, Tsukuba-Shi, Ibaraki 305-0035 (FR). TSUKADA, Eri [JP/JP]; Amour Liberte 18, 306, 2-13-3 Matsushiro, Tsukuba, Ibaraki 305-0035 (JP). GIRARD, Jean-Marc [FR/FR]; 12, rue Michel Chasles, F-75012 Paris (FR).


(74) Agents: VESIN, Jacques et al.; c/o L'air Liquide S.A., Direction de la Propriété Intellectuelle, 75, quai d'Orsay, F-75321 Paris Cedex 07 (FR).

(71) Applicant (for all designated States except US): L'AIR LIQUIDE, SOCIETE ANONYME A DIRECTOIRE ET CONSEIL DE SURVEILLANCE POUR L'ETUDE ET L'EXPLOITATION DES PROCEDES GEORGES CLAUDE [FR/FR]; 75, quai d'Orsay, F-75321 Paris Cedex 07 (FR).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,

[Continued on next page]

(54) Title: METHOD FOR FORMING DIELECTRIC OR METALLIC FILMS



(57) Abstract: Method for producing a metal silicon (oxy)nitride by introducing a carbon-free silicon source (for example, $(\text{SiH}_3)_3\text{N}$), a metal precursor with the general formula MX_n (for example, $\text{Hf}(\text{NEt}_2)_4$), and an oxidizing agent (for example, O_2) into a CVD chamber and reacting same at the surface of a substrate. M_2SiN , MSiO and/or MSiON films may be obtained. These films are useful as high k dielectrics films.



MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

- (84) **Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.